



TEST REPORT

APPLICANT: HANWHA L&C CORPORATION REPORT NO. : D270-15-01312

SAMPLE RECEIVED DATE : 2015-08-03 REPORT ISSUED DATE : 2015-08-17

PAGE : 1 OF 3

SAMPLE DESCRIPTION: ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE INTERIOR FILM.

ITEM : BODAQ INTERIOR FILM Z825S

TEST CONDUCTED: AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

PREPARED AND CHECKED BY

Seongkeum Jang

FOR FITI

SEONG-KEUN, JANG QUALITY MANAGER AUTHORIZED BY FOR FITI

moon Ou noh

MOON-OK NOH PRESIDENT

★ Report Verification No.: 5G4P-6FPV-9JRR ★

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)



www.fiti.re.kr

ш 1

REPORT NO.: D270-15-01312

PAGE : 2 OF 3

TEST CONDUCTED

TEST RESULT

DI ANIZ

(01) ANTIMICROBIAL ACTIVITY AND EFFICACY (JIS Z 2801 : 2010, FILM-CONTACT METHOD)

: CFU/cm², VALUE OF ANTIMICROBIAL ACTIVITY log

		DLAINN	# 1
BACTERIA-1:	AT BEGINNING	1.3×10^4	1.3×10^4
	AFTER 24 h	1.9 X 10 ⁴	7.5 X 10
	VALUE OF ANTIMICROBIAL ACTIVITY	_	2.4
BACTERIA-2:	AT BEGINNING	1.3×10^4	1.3×10^4
	AFTER 24 h	9.4×10^5	4.6×10^{2}
	VALUE OF ANTIMICROBIAL ACTIVITY	_	3.3

NOTE) · STANDARD FILM : STOMACHER®400 POLY-BAG

 \cdot TEST CONDITION : THE SOLUTION ARE FIXED AT (35 \pm 1) $^{\circ}$ C, 90 $^{\circ}$ C, R.H. FOR 24 h,

AND DETERMINE BACTERIA CELL GROWTH INHIBITION RATE BY POUR AGAR PLATE METHOD.

• TEST BACTERIA : BACTERIA-1 - Staphylococcus aureus ATCC 6538P

BACTERIA-2 - Escherichia coli ATCC 8739

· ANTIMICROBIAL EFFICACY: THE VALUE OF ANTIMICROBIAL ACTIVITY SHALL NOT BE LESS THAN 2.0 log

· EXCLUSIVE OF PAPER LINER

· SEE ATTACHED PHOTOS

- SAMPLE PHOTO -



e-DOCUMENT SERVICE •



www.fiti.re.kr

REPORT NO.: D270-15-01312

PAGE : 3 OF 3

TEST CONDUCTED TEST RESULT

- BACTERIA-1 : BLANK - - B





- BACTERIA-2 : BLANK -

- BACTERIA-2 : #1 -





e-DOCUMENT SERVICE •